# LATEX GLOVE POWDER-FREE

## **FUNCTIONAL BENEFITS**

- Protection from unwanted or dangerous substances
- Easy donning and helps prevent roll back
- Softness provides superior comfort and natural fit
- Beaded cuff makes donning easy
- Ambidextrous and straight fingers





### **Quality Standards**

- Conforms to ASTM D3578 and EN455 Standards
- Manufactured under QSR (GMP), ISO9001:2008 and ISO13485:2003 Quality Management System
- Using FDA approved absorbable corn starch, USP grade
- Conforms to MDD 93/42/EEC Class I

#### **Glove Sizes**

- Extra-small, Small, Medium, Large, Extra-large
- Marked in the check box on the shipping carton with black ink

## **Product Specifications**

Type : Powder-free, non-sterile

Material : Natural high quality latex

Design & Features : Powder-Free (Polymer Coated or Online Chlorinated

Ambidextrous, smooth or textured surface; beaded cuff;

off-white to yellow, coloured or mint flavoured

Storage : To store in a cool and dry condition

Shelf-life : 5 years from the date of manufacturing



# PHYSICAL DIMENSIONS

DIMENSIONS	STANDARDS		
	VOLEIN	ASTM D3578	EN455
Length (mm)	240 min	220 min (XS, S) 230 min (M, L)	240 min
Width (mm)  • Extra Small  • Small  • Medium  • Large  • Extra Large	76 ± 3 84 ± 3 94 ± 3 105 ± 3 113 ± 3	70 ± 10 80 ± 10 95 ± 10 111 ± 10 N/A	≤ 80 80 ± 10 95 ± 10 110 ± 10 ≥ 110
Thickness – Single Wall (mm) • Fingers • Palm	0.08 min 0.08 min	0.08 min 0.08 min	N/A N/A

# PHYSICAL PROPERTIES

PROPERTY	<b>ASTM D3578</b>	EN455
Elongation at Break (%)  • Before Ageing	650 min	NI/A
After Ageing	500 min	N/A N/A
Tensile Strength (MPa)  • Before Ageing  • After Ageing	18 min 14 min	N/A N/A
Median Force at Break (N)  • Before Ageing  • After Ageing	N/A N/A	6 6



